


SGS U.S. Testing Company Inc.

291 Fairfield Avenue
Fairfield, NJ 07004
Tel: 973-575-5252
Fax: 973 575-0799

REPORT NUMBER: 126786
REF. #: 518718
DATE: July 14, 1999
PAGE: 1 of 3

CLIENT: Crane Kemlite
23525 W. Eames
Channahon, IL 60410

Attn: Molly Dickerman

AUTHORIZATION: Letter of authorization received from Molly Dickerman of Crane Kemlite

SAMPLE DESCRIPTION: Five (5) samples received from the client on June 28, 1999. Client identified the samples as:

1. K990616 - 1 & 2, 285 LTR
2. K990616 - 3 & 4, 385 LTR
3. K990616 - 5 & 6, 485 LTR
4. K990616 - 7 & 8, 385 LTR Alternate Resin
5. K990616 - 9 & 10, Kemply 0.09 "PWI on 3/8" Plywood

TEST REQUESTED: Selected test as listed on the following page.

TEST DATES: July 9 - 13, 1999.

RESULTS: Continued on Page 2.

PREPARED BY:

Linda Kinderman

Linda Kinderman
Technician - Flammability
Textile Services

mh

SIGNED FOR COMPANY BY:

Edward McCarthy
Supervisor Flammability
Textile Services

Member of the SGS Group

ANALYTICAL SERVICES • PERFORMANCE TESTING • STANDARDS EVALUATION • CERTIFICATION SERVICES
SGS U.S. TESTING COMPANY INC. REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANYONE RELYING ON SUCH REPORTS SHOULD UNDERSTAND ALL OF THE DETAILS OF THE ENGAGEMENT. REPORTS REFLECT RESULTS ONLY OF THE STANDARDS OR PROCEDURES IDENTIFIED TO THE TESTS CONDUCTED AND ARE LIMITED TO THE SAMPLES TESTED. TEST RESULTS MAY NOT BE INDICATIVE OF THE QUALITIES OF THE LOT FROM WHICH THE SAMPLE WAS TAKEN. SGS U.S. TESTING COMPANY INC. HAS NOT CONDUCTED ANY QUALITY CONTROL PROGRAM FOR THE CLIENT. NEITHER THE NAME, SEALS, MARKS NOR INSIGNIA OF SGS U.S. TESTING COMPANY INC. MAY BE USED IN ANY ADVERTISING OR PROMOTIONAL MATERIALS WITHOUT THE PRIOR WRITTEN APPROVAL OF SGS U.S. TESTING COMPANY INC. THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL WITHOUT THE WRITTEN PERMISSION OF THE SGS U.S. TESTING COMPANY INC. SAMPLES NOT DESTROYED IN TESTING ARE DISPOSED OF AFTER 30 DAYS.

REPORT OF TEST



SGS U.S. Testing Company Inc.

REPORT NUMBER: 126786

REF. #: 518718

DATE: July 14, 1999

PAGE: 2 of 3

CLIENT: Crane Kemlite

RESULTS:

Flammability of Interior Materials

FMVSS 302-1992

Sample: K990616 - 1 & 2, 285 LTR

Burn Time* (secs)		Burn Distance (in)		Burn Rate (in/min)	
MD	XMD	MD	XMD	MD	XMD
300.0	300.0	4.5	5.9	0.9	1.2
300.0	300.0	4.7	6.0	0.9	1.2
300.0	300.0	4.2	5.6	0.8	1.1

Sample: K990616 - 3 & 4, 385 LTR

300.0	300.0	3.4	4.2	0.7	0.8
300.0	300.0	3.4	4.4	0.7	0.9
300.0	300.0	3.6	3.8	0.7	0.8

Sample: K990616 - 5 & 6, 485 LTR

300.0	300.0	2.3	3.1	0.5	0.6
300.0	300.0	2.8	3.5	0.6	0.7
300.0	300.0	3.1	3.1	0.6	0.6

Sample: K990616 - 7 & 8, 385 LTR alternate resin

300.0	300.0	4.2	3.9	0.8	0.8
300.0	300.0	3.9	3.6	0.8	0.7
300.0	300.0	4.0	3.5	0.8	0.7

REPORT OF TEST



REPORT NUMBER: 126786
REF. #: 518718
DATE: July 14, 1999
PAGE: 3 of 3

CLIENT: Crane Kemlite

RESULTS:

Flammability of Interior Materials
FMVSS 302-1992

Burn Time* (secs)		Burn Distance (in)		Burn Rate (In/min)	
MD	XMD	MD	XMD	MD	XMD
Sample: K990616 - 9 & 10, (Kemply 0.09" PWI on 3/8" Plywood)					
DNI	DNI	-	-	-	-
DNI	DNI	-	-	-	-
DNI	DNI	-	-	-	-

*Test was discontinued after 5 minutes

DNI = Does Not Ignite

Requirements:

The material shall not burn or transmit a flame front across its surface, at a rate of more than 4 inches per minute. However, if a material stops burning before it has burned for 60 seconds from the start of timing and has not burned more than 2 inches from the point where timing was started, it shall be considered to meet this requirement.

Conclusion:

The submitted samples meet the requirement of the Department of Transportation Motor Vehicle Safety Standard 302 "Flammability of Interior Materials"

End of Report

REPORT OF TEST